



CG2 Wide Joint Grout

**Flexible Wide Joint
Wall & Floor Grout 2-20mm, 10kg**

2-20mm Joint Width / 45 mins Open Time / 24 hours Set Time

- Natural Stone
- Ceramic / Porcelain / Mosaics
- Timber / Underfloor Heating
- Swimming Pools / Wet Areas
- Anti-Fungal
- Internal / External



DESCRIPTION

ROCATEX CG2 Wide Joint Grout is a cement based anti-fungal powdered grout. This highly flexible wall and floor grout has been developed for tiles with joint widths between 2-20mm and is ideal for internal and external use in both wet and dry conditions, including swimming pools.

ROCATEX CG2 Wide Joint Grout is suitable for grouting joints between ceramic, porcelain, natural stone, quarry, marble and mosaic tiles.

DO NOT apply if frost is forecast within 24 hours, in wet conditions, in temperatures below +5°C or above +25°C, to areas in direct sunlight or to substrates that are hot.

A grout film and/or pigment stains, especially with dark colours, may remain on unglazed or matt glazed tiles and flags after grouting. Follow the tile manufacturer's recommendations. A trial grouting area is recommended to check suitability.

Only clean water and clean tools must be used for grouting and final cleaning. Never add water or fresh grout and/or powder to a grout mix which has already started to set.

PREPARATION

Ensure the tiles are firmly fixed and the joints are clean, free of dust, excess adhesive, bedding mortar, grease or any contamination.

MIXING

Mix 10kg of ROCATEX CG2 Wide Joint Grout with approximately 2.4 litres of cold clean water until a smooth creamy consistency is achieved using a suitable drill with whisk attachment, mix for 2 minutes until a slump-free creamy mortar is produced. Allow to stand for 2 minutes then re-mix.

APPLICATION

Use a rubber float to work the grout deeply into the joints until flush with the tile. Excess grout should be removed as work proceeds and any residues left on the tile face can be removed by wiping off with a damp sponge 15-30 minutes after application. Any dry film remaining on the surface can be removed by polishing off with a dry cloth when the grout has hardened in the joints.

COVERAGE

Coverage is dependent on the tile dimensions and joint width. It can be calculated using the formula below, all measurements in mm.

- Add: length and breadth of tile together
- Multiply: result by joint width
- Multiply: result by joint depth
- Multiply: result by 1.6 (coverage figure for ROCATEX CG2 Wide Joint Grout)
- Divide: result by length of tile
- Divide: result by breadth of tile

The result is the material requirement in kg per square metre.

$$\frac{(A+B) \times C \times D \times 1.6}{A \times B} = \text{kg/m}^2$$

TECHNICAL DATA

Conformity:	Conforms to the requirements of EN 13888
Class:	CG2
Application temperature:	5°C to 25°C
Mixing ratio:	2.4 litres of water to 10kg powder
Open time:	45 mins at 20°C
Set time:	3 hrs at 20°C (walk on) 24 hrs at 20°C (full cure)
Joint width:	2-20mm
Protein free:	Yes
Shelf life:	12 months in cool dry area
Sizes:	10kg

STORAGE

Store unopened in a cool dry, frost free environment.

HEALTH & SAFETY INSTRUCTIONS



Health & safety advice, which must be followed, can be found on the Material Safety Data Sheet. Users are advised to wear face mask, goggles, gloves and overalls when handling, mixing and applying cementitious products.

Contains Portland Cement. Contains Chromium (VI), which may produce an allergic reaction. Clothing contaminated by wet cement should be removed immediately and washed before re-use. R38 - Irritating to skin. R41 - Risk of serious damage to eyes. S26 - In case of contact with eyes, rinse immediately with water and seek medical advice. S37/39 - Wear suitable gloves and eye/face protection. S2 - Keep out of reach of children.

For further information, please request the Material Safety Data Sheet for this product.